




Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

E 1299 / 17759



E J K U

Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

98202723.7

PRIORITY
DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts:
im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

I.L.C. HATTEN-HECKMAN

DEN AAG, DEN
HE GUE,
H E, LE

04/10/99



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

Blatt 2 der Bescheinigung
Sheet 2 of the certificate
Page 2 de l'attestation

Anmeldung Nr.:
Application no.: 98202723.7
Demande n°:

Anmeldetag:
Date of filing: 14/08/98
Date de dépôt:

Anmelder:
Applicant(s):
Demandeur(s):
Rockwool International A/S
2640 Hedehusene
DENMARK

Bezeichnung der Erfindung:
Title of the invention:
Titre de l'invention:
Mineral wool plant substrate

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s) revendiquée(s)

Staat:
State:
Pays:

Tag:
Date:
Date:

Aktenzeichen:
File no.
Numéro de dépôt:

Internationale Patentklassifikation:
International Patent classification:
Classification internationale des brevets:
A01G31/00

Am Anmeldetag benannte Vertragsstaaten:
Contracting states designated at date of filing: AT/BE/CH/CY/DE/DK/ES/FI/FR/GB/GR/IE/IT/LI/LU/MC/NL/PT/SE
Etats contractants désignés lors du dépôt:

Bemerkungen:
Remarks:
Remarques:

MINERAL WOOL PLANT SUBSTRATE

The present invention relates to a mineral wool plant substrate, more in particular to a mineral wool plant substrate comprising a foreign material or materials in order to improve the properties of the mineral wool substrate to realize Crop Protection and/or improve plant performance in relation to additions (such as nutrients, pesticides, water and the like) as applied by growers during a cropping cycle.

Mineral wool plant substrates for plant growth are well-known in the art and consist of a coherent matrix of mineral wool. This coherent matrix is formed by collecting a layer of mineral wool fibres provided with a curable binder, so that after curing the mineral wool fibres are substantially not displaceable relative to one another. If required for fast uptake of water this coherent matrix of mineral wool may be provided with a wetting agent.

Under mineral wool is to be understood glass wool, stone wool, rock wool, man made vitrous fibres, slag wool, and/or mixtures thereof.

The fibres may have an average diameter varying in between 1-10 μm . For rock wool the fibre diameter is on average about 4 μm .

The density of the coherent matrix of mineral wool may be between 10-200 kg/m^3 , in general in the range of 40-80 kg/m^3 .

Such a coherent matrix of mineral wool has a form retaining property, which is inherent due to the inorganic starting materials used. Furthermore, the water retaining capacity of these mineral wool plant substrates is very well controllable and predictable.

A problem is that growers, utilizing such mineral wool plant substrates may inadvertently stress and even damage plants by overdosing or underdosing the mineral wool substrates with additions, such as nutrient

solutions, when considering plant requirements at a certain time and growth stage.

An object of the present invention is to provide an improved mineral wool plant substrate, which
5 aims to overcome this problem.

According to a first aspect of the present invention there is provided a mineral wool plant substrate according to claim 1.

In soil plants extract their necessary
10 compounds such as essential nutrients from available compounds in the soil water. If the amount of compounds in the soil water either exceeds or is less than the amount required by the plant, these compounds will be
15 respectively released or stored on charged soil particles. This can be quantified as the ion exchange capacity (IEC). These soil particles may contain both a fixed and/or a variable IEC (variable meaning that the amount of IEC is dependent on other parameters such as
20 pH, water content and structure).

The mechanism of release and storage is based
25 on the chemical equilibria of compounds between soil particles and the soil water solution and/or soil particles and soil air solution.

This IEC and the mechanism for release and
30 storage of compounds in soils not only works for ions, but is also appropriate for compounds which are electrically neutral, but due to their chemical structure contain strong positive and negative dipole charges, examples being water and organic compounds such as
35 carbon-acids and alcohols.

This mechanism for exchanging and storage of compounds and IEC is however lacking in mineral wool plant substrates. Therefore, if growers over or underdose mineral wool substrates with for example nutrients and
35 pesticides, this can have a severe negative effect on the plants (such as stress, damage and the like) resulting in a suboptimal growth response, both qualitatively and

quantitatively. The plant stress induced in this way, can even result in the induction of plant diseases.

The inventors have shown that by adding an ion exchange agent containing a fixed and/or variable IEC to 5 mineral wool plant substrates, vital compounds are buffered therewithin. This means that if a grower adds an over or under dose of compounds to the plant substrate the plant is substantially prevented from negative effects thereby.

10 The ion-exchange agent is preferably a cation exchange-agent which comprises soil minerals, and most preferably exhibits a non-clay like behaviour with respect to swelling and shrinkage.

Micro-organisms can be very important to the 15 growth of the plant. On the one hand such organisms play a role in plant protection, for example the occurrence plant diseases induced by pathogens and/or predators (such as phythium and Protozoa) are prohibited by both optimized crop conditions (such as sufficient nutrients) 20 and the appearance of antagonists, i.e. micro-organisms, of these pathogens and predators, and on the other hand, micro-organisms (such as mycorizha) can live in symbioses with the plant and in this way induce improved plant growth.

25 A good habitat for micro-organisms is available in materials containing pores with an average size of 6 μm or less. Very good conditions are provided when the pores are smaller than 3 times the size of the micro-organisms, yet still larger than the organisms. Clay 30 (such as Bentonite) is an example of a material containing an average pore size $< 6 \mu\text{m}$. The porosity and average pore size of clay is not static but fluctuates considerably due to the swell and shrink behaviour of clay, which is influenced, amongst other things by the 35 pH-level, EC-level and water content.

Plant pathogens and predators are bigger in size than known antagonist and plant beneficial micro-

organisms. The latter are therefore more likely to profit from this smaller pore size.

In mineral wool plant substrates having a density of 10-200 kg/m³ the average pore size is most likely to be larger than 10 µm. Mineral wool plant substrates have a stable structure and porosity and are substantially not sensitive to swell and shrink behaviour.

In order to improve the mineral wool plant substrate as a microbiological habitat, especially for plant protective micro-organisms, the ion-exchange agent preferably has an average pore size smaller than a mineral wool substrate of about 72 kg/m³ (which has approximately an average pore size of 25 µm), preferably also exhibits less swelling and shrinkage than clay and most preferably has an average pore size < 6 µm.

Most preferably the ion-exchange agent comprises a zeolite. Since zeolites have a stable, cage like structure they offer an ideal, stable habitat for micro-organisms.

The substrate may further more comprise an organic substance like peat, coco, sphagnum or several types of compost, preferably to a degree of humification of 10-70%, more preferably comprising 10-60% humic acids and/or nitrogen compounds (such as proteins, amino acids and amides) and most preferably originating from a natural source, which can substitute the mineral wool for upto 20 volume %, preferably upto 10 volume %.

Suitable organic substances are referred to in WO 96/33602 which are included herein by reference.

PH control in cropping is often required for a good growth response. However, with mineral wool plant substrates good pH control is difficult to achieve. The pH resulting from the nutrient solution (based on the required pH plant growth) often differs from the actual found pH in the mineral wool substrate. This is due to several reasons.

Firstly the mineral wool plant substrat behaves basic chemically, and therefore the pH in the substrate increases.

Secondly plants extrudate organic substances from their surroundings which can influence pH.

Uptake of nutritional ions leads to the exclusion of H^+ and OH^- by plant roots which can also influence the pH. Furthermore the state of the plant conditions, i.e. considering factors such as induced stress can also influence the type and amount of nutrient uptake and exclusion of extrudates.

Organic substances are good at buffering H^+ ions via ad- and de-sorption of NH_2 groups and buffering of OH^- ions via carbon-acid like groups (such as fulvic and Humic acids).

Organic matter is also susceptible to biological degradation, affecting structure, amount and function of the effective pH buffering groups and therefore the pH buffering capacity of the organic matter. The degree of humification of organic substances is an indication for the possible degree and amount of degradation. Substances with a low degree of humification are more likely to degrade than substances with a high degree humification. However, by using biologically degradable organic substances the mineral wool plant substrate provides further advantageous properties linked to the organic substance, being the provision of a carbon source. Further, due to the degradation of the organic substance plant stimulating compounds are released such as humic acids and vitamins which are beneficial to plant growth. Chelate forming compounds which keep slight or insoluble trace elements in the nutrient solution may also be released. The organic substance preferably has a degree of humification varying between 10-70% in order to provide good pH buffering and positive effects on degradation.

When it is desired to provide a mineral wool plant substrate with an improved water buffering capacity

with higher available amounts of water between pF 0.5 and 2 and/or a more intermediate and fixed IEC, it is worthwhile to partially substitute the mineral wool by an inorganic substance such as a natural clay. The clay may substitute the mineral wool for up to 20 volume %.

Clay for substitution of the organic substance may comprise soil materials comprising hydrophilic particles preferably having a particle size below 20 μm , such particles, for example, belonging to the class of eroded minerals, such as clays, mixtures of clays with silt and sand having a clay fraction removable as sludge of at least 20%, and further bentonite, kaolin and the like. Particularly suitable are different naturally occurring types of clays or mixtures thereof, such as young sea clay. Examples are clays comprising 0-100%, preferably 10-50% of particles having a size preferably being smaller than 20 μm .

The use of clay provides another advantage when the organic substance is included in the matrix in the form of a pellet. In this situation clay functions as a lubricating agent and as a material that reduces the compressibility of the pellet.

The combination of clay and organic matter forms a so called clay-humus complex which can lead to an improved physical structure i.e. increased porosity, increased pore sizes and therefore a drier, more aerated structure.

Accordingly, the amount of clay may be used in order to change the biodegradable character of the organic substance used. For example peat which is normally biodegradable may rendered substantially biodegradable due to the addition of clay to the pellet.

In this manner, clay may inhibit or retard the biodegradation of the inorganic substance.

The pellet may have a (particle) size of about 0.1-20 mm.

Due to the presence of clay and of peat the concentration of spore elements in the water residing within the mineral wool matrix may be controlled, due to

the sustained release of cations temporarily stored within the organic substance and/or clay.

The invention will now be further elucidated by reference to the following examples.

5

Example 1

A coherent growth substrate was prepared having the form of grow-blocks (10*10*6.5 cm) consisting of a coherent matrix of mineral wool to which a phenol-
10 formaldehyde based binding agent and a wetting agent was applied. Prior to passage through a curing oven, zeolite in a quantity of 10 weight % (particle size 2-6 mm having a cation exchange Capacity of 80 meq/100 gram dry matter) was added to the matrix. The density of the coherent
15 growth substrate amounted to 80 kg/m³. The CEC of the coherent growth substrate based on volume contained a CEC of 3-6 mmol/litre substrate. This buffer capacity was 12-25% of the optimal applied nutrient solution.

20 Example 2

A coherent growth substrate was prepared having the form of grow-blocks (10*10*6.5 cm) consisting of a coherent matrix of mineral wool to which a furan based binding agent was applied.

25

(Binding agents as described in WO 97/07664 are included herewith by reference)

Prior to passage through a curing oven, an equal mixture of 50% zeolite and 50% clay, which together
30 formed a quantity of 10 weight % was added to the matrix. The density of the coherent growth substrate amounted to 80 kg/m³.

The CEC of the Zeolite was 80 meq/100 gram dry matter, particle size was 2-6 mm, and the average pore
35 size was < 10 µm.

The CEC of the Clay was 20 meq/100 gram dry matter, particle size was 2-6 mm and the average pore size was 5-12 µm.

14 AUG '98 16:16

ARNOLD&SIEDSMA +5136234312

ARNOLD&SIEDSMA

8

The average pore size of mineral wool matrix lay between 15-30 μm .

The CEC of the coherent growth substrate based on volume of the substrate contributed to a total CEC of 5 2-4 mmol/liter substrate. This buffer capacity was 8-16% of the optimal applied nutrient solution.

Based on the volume of the coherent substrate, less than 1% of the total volume of the substrate contained an average pore size of less than 12 μm .

10 The inventors have shown that was sufficient to establish two different ecological niches for micro-organisms of differing sizes compared to products without the addition of the ion exchange agent exhibiting only one ecological niche.

15 The added amount of clay contributed in an extra absolute amount of water of 1-2 volume% in pF range 0.5-1.5. The relative extra amount of water available in this pF range, increased from 2% for pF 0.5 to 14% for pF 1.3. Research indicated that the extra available amount
20 of 1.5% in clay induced an improved growth response for cucumbers of 3-4% in the first 30 days of growth when applying a water regime lying between pF 1 and 1.3.

Example 3

25 A coherent growth substrate was prepared having the form of grow-slabs (100*15*7.5 cm) which consisted of a coherent matrix of mineral wool to which a Phenol-Formaldehyde based binding agent and wetting agent were applied. Prior to passage through a curing oven, a
30 mixture of 90% zeolite and 10% organic matter, together forming 12 weight % was added to the matrix. The density of the coherent growth substrate amounted to 57 kg/m³.

The CEC of the Zeolite was 80 meq/100 gram dry matter, particle size was 2-6 mm and the average pore
35 size was < 10 μm .

The organic matter comprised more than 10% humic acid.

The average pore size of mineral wool matrix lay between 20-35 μm .

The CEC of the coherent growth substrate based on volume of the substrate contributed to a total CEC of 2-4.5 mmol/litre substrate. This buffer capacity was 8-16% of the optimal applied nutrient solution.

Based on the volume of the coherent substrate, less than 0.5% of the total volume of the substrate contained an average pore size of less than 10 μm .

10 Research indicated that this is sufficient to establish two different ecological niches for micro-organisms of differing sizes compared to products without the addition of the ion exchange agent exhibiting only one ecological niche.

15 The invention is not limited to the above description; the requested rights are rather determined by the following claims.

CLAIMS

1. Mineral wool plant substrate comprising a coherent matrix of mineral wool and upto 20 volume % of an ion-exchange agent comprising a variable and/or fixed ion-exchange capacity of about 15, preferably 30 and most
5 preferably 40meq/100g dry weight or more.

2. Substrate according to claim 1 wherein the ion-exchange agent is a cation-exchange agent.

3. Substrate according to claims 1 or 2 wherein the ion-exchange agent comprises soil minerals.

10 4. Substrate according to claims 1, 2 or 3 wherein the ion-exchange agent has a non-clay like behaviour with respect to swelling and shrinkage, and preferably has a stable zeolite, cage-like structure.

5. Substrate according to any of the previous
15 claims wherein the ion-exchange agent has an average pore size smaller than the average pore size of mineral wool having a density of less than about 72 kg/m³.

6. Substrate according to any of the previous claims wherein the ion-exchange agent comprises a
20 zeolite.

7. Substrate according to any of the previous claims further comprising an organic substance, preferably comprising sphagnum, peat, substituting the mineral wool for upto 20 volume %, preferably upto 10
25 volume %.

8. Substrate according to any of the previous claims further comprising clay, substituting the mineral wool for up to about 20 volume %.

9. Substrate according to any of the previous
30 claims for use as a growing block.

10. Substrate according to any of the claims 1-8 for use as a growing mat.

14-08-1998

EP98202723.7

SPEC

14 AUG '98 16:17

ARNOLD&SIEDSMA +31302545372

P.16

ARNOLD&SIEDSMA

2

11. Substrate comprising a coherent matrix of mineral wool, a pre-determined amount of clay and a pre-determined amount of an organic substance, preferably comprising sphagnum, peat, substituting the mineral wool for upto 20 volume %, preferably upto 10 volume %.

ABSTRACT

The invention relates to a mineral wool plant substrate comprising a coherent matrix of mineral wool and upto 20 volume % of an ion-exchange agent comprising a variable and/or fixed ion-exchange capacity of about 5 15, preferably 30 and most preferably 40meq/100g dry weight or more.